











5cm Technical Features








PORCELAIN PAVERS

 GL-UGL	THICKNESS		50 mm		
 GL-UGL	WATER ABSORPTION	ISO 10545-3 CLASSE B1A ASTM C 373 (E<=0,5%)	COMPLIANT		
 GL-UGL	FROST RESISTANCE	EN 202 ISO 10545-12 ASTM C 1026	FROST RESISTANT		
 GL-UGL	BENDING STRENGTH	ISO10545-4		Size 8"x16"	Size 16"x24"
			~ 71.673N	~ 71.660N	~ 70.000N
 GL-UGL	BREAKAGE LOAD F AVERAGE VALUE (N)	ISO10545-4	~ 49.000N/mm ²	~ 48.500 N/mm ²	~ 48000N/mm ²
	MODULUS OF RUPTURE R AVERAGE VALUE (N/mm²)		~ 47,5 N/mm ²	~ 47,5 N/mm ²	~ 47,00 N/mm ²
 GL	CHEMICAL RESISTANCE	ISO 10545-13 ASTM C 650	GA-GLA GHA		
 GL-UGL	ANTI-GLISSANT	DIN 51130 R	≥11		
		COEFFICIENTE D'ATTRITO BCR TORTUS	DRY ≥0,60 - WET ≥0,60		
		ASTM C 1028 C.O.F.	DRY ≥0,60 - WET ≥0,60		
		DCOF (BOT 3000) SECTION 9.6 ANSI 137.1 2012)	WET >0,42		
 GL-UGL	SALT RESISTANCE	NaCl	RESISTANT		

Salt leaves a residual of white colour that can be removed with fresh water and scrubbing brush. Scrub until the total removal of the residual.



6.5cm Technical Features

PORCELAIN PAVERS		Sizes 4"x4"/4"x8"/8"x8"	
 GL-UGL	THICKNESS		65 mm
 GL-UGL	WATER ABSORPTION	ISO 10545-3 CLASSE B1a ASTM C 373 (E<=0,5%)	CONFORME
 GL-UGL	FROST RESISTANCE	EN 202 ISO 10545-12 ASTM C 1026	INGELIVO
 GL-UGL	UNIAXIAL COMPRESSIVE LOADING (N/mm ²)	UNI EN 1926/2000	132 N mm ²
 GL	CHEMICAL RESISTANCE	ISO 10545-13 ASTM C 650	GA-GLA GHA
 GL-UGL	ANTI-GLISSANT	DIN 51130 R	≥11
		COEFFICIENTE D'ATTRITO BCR TORTUS	DRY ≥0,60 - WET ≥0,60
		ASTM C 1028 C.O.F.	DRY ≥0,60 - WET ≥0,60
		DCOF (BOT 3000) SECTION 9.6 ANSI 137.1 2012)	WET >0,42
 GL-UGL	SALT RESISTANCE	NaCl	RESISTANT

Salt leaves a residual of white colour that can be removed with fresh water and scrubbing brush. Scrub until the total removal of the residual.



PACKING LIST

**BASALTO, PORFIDO,
CEMENTO, GRANITO**

50 mm

		PZ/PAL	MQ/PAL	KG/PZ	KG/PAL
20x40	8"x16"	120	9,6	9,15	1120
40x60	16"x24"	40	9,6	27,50	1120
60x60	24"x24"	28	10,08	41,30	1156

- F.to 20x40x5> Pallet cm 85x125
- F.to 40x60x5>Pallet cm 85x125
- F.to 60x60x5>Pallet cm 65x125

*The weight of the pallet is to be understood as the sum of the weight of the pallets and the goods.

**LAPIS LUX, LAPIS NERO,
LAPIS RUBRA**

65 mm

		PZ/PAL	MQ/PAL	KG/PZ	KG/PAL
10x10	4"x4"	768	7,68	1,50	1167
10x20	4"x8"	384	7,68	3,00	1167
20x20	8"x8"	192	7,68	6,00	1167

*The weight of the pallet is to be understood as the sum of the weight of the pallets and the goods.

The above mentioned weights may change for technical reasons for +/- 4%./